

DESCRIPTION

Double Coat Anti-slip powder is a special additive based on a polyethylene granulate.

PRINCIPAL CHARACTERISTICS

- Used as anti-slip powder for Double Coat or Double Coat Dubbel UV;
- Colourless, the colour of the final coat will not change;
- Easy to clean;
- Recommended for all surfaces where an anti-slip profile is required, such as decks, gangways, shower rooms, etc.

COLOURS AND GLOSS

Colourless

BASIS PROPERTIES (AT 23 °C AND 50% R.H.)

Density : approx. 0,9 g/cm³
 Solid content : approx. 100 % (volume)
 Shelf life : separate components, stored cool an dry in original packaging, minimum 24 months
 Flash point (DIN53213) : n.a.

INSTRUCTIONS FOR USE

- Mask the area to be treated with Double Coat Anti-slip powder with a suitable masking tape.
- Mix both components Double Coat or Double Coat Dubbel UV (base and hardener) thoroughly. When required add some Double Coat Brush thinner.
- Next add carefully Double Coat Anti-slip powder to the mixture Double Coat.
- Stir the mixture at regular interval to avoid settling.
- Apply in an even film using a suitable foam or mohair roller. Do not apply a too heavy coat, this will result in an uneven film. Remove masking tape immediately after application.
- For details on application, please consult the technical datasheet of Double Coat or Double Coat Dubbel UV.

Mixing ratio : 5,0 parts powder : 100,0 parts Double Coat or Double Coat Dubbel UV (by weight)
 The mixing ratio by volume depends on colour.
 Do not prepare more material than can be applied within the pot life of the mixture.

Induction time : see technical datasheet Double Coat or Double Coat Dubbel UV
 Pot life : see technical datasheet Double Coat or Double Coat Dubbel UV

Application with :

	Brush/roller
Type thinner	Brush thinner
% of thinner	3 - 5 %
Nozzle orifice	n.a.
Nozzle pressure	n.a.
Cleaning	Brush thinner

SAFETY INFORMATION

See the corresponding Material Safety Data Sheet for detailed instructions on safety, disposal and health.

Date: September '14
706-00000

Disclaimer

Although the information and recommendations are presented in good faith and believed to be correct at date of issue, De IJssel Coatings B.V. makes no representations as of the completeness or accuracy thereof. In no event De IJssel Coatings B.V. will be responsible for damages of any nature whatsoever resulting from the use of this information.